

# Salflex 623TIM

Polypropylene Copolymer

Salflex Polymers Ltd.

Message:

Salflex 623TIM is a polypropylene copolymer (PP Copoly) product, which contains 10% talc filler. It can be processed by injection molding and is available in North America. Salflex 623TIM applications include the automotive industry and electrical appliances. The main characteristics are: impact resistance.

General Information			
Filler / Reinforcement	Talc filler, 10% filler by weight		
Features	Impact resistance, high		
Uses	Home appliance components		
	Application in Automobile Field		
	Car interior equipment		
	Car dashboard		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ISO 1133
Molding Shrinkage	0.90	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	74		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Flexural Modulus	2150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	37	kJ/m <sup>2</sup>	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	118	°C	ISO 75-2/B
Additional Information			
Ash Content, ISO 3451/1A: 24%			
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	190 - 220	°C	
Middle Temperature	200 - 230	°C	
Front Temperature	210 - 235	°C	
Nozzle Temperature	215 - 240	°C	

Processing (Melt) Temp	200 - 220	°C
Mold Temperature	27.0 - 60.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

