

NORYL GTX™ GTX830 resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics

Message:

NORYL GTX830 a 30% glass reinforced grade which offers an excellent combination of chemical/heat resistance in combination with stiffness.

General Information			
UL YellowCard	E45329-236571		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Rigidity, high		
	Good chemical resistance		
	Heat resistance, high		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.32	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	7.00	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.20 - 0.30	%	Internal method
Transverse flow: 3.20mm	0.80 - 1.0	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	3.1	%	ISO 62
Equilibrium, 23°C, 50% RH	1.1	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7300	MPa	ISO 527-2/1
Tensile Stress (Break)	110	MPa	ISO 527-2/5
Tensile Strain (Break)	2.5	%	ISO 527-2/5
Flexural Modulus ¹	6200	MPa	ISO 178
Flexural Stress	170	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/2C
-20°C	7.0	kJ/m ²	ISO 179/2C
23°C	7.0	kJ/m ²	ISO 179/2C
Charpy Unnotched Impact Strength ²			ISO 179/1eU
-30°C	40	kJ/m ²	ISO 179/1eU
23°C	60	kJ/m ²	ISO 179/1eU

Unnotched Izod Impact Strength ³			ISO 180/1U
-30°C	45	kJ/m ²	ISO 180/1U
23°C	45	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	220	°C	ISO 306/B50, ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 60°C	2.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 60°C	8.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.26	W/m/K	ISO 8302
RTI Elec	120	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI	125	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	HB		UL 94
3.00 mm	HB		UL 94
Oxygen Index	29	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.070	%	
Hopper Temperature	60.0 - 80.0	°C	
Rear Temperature	260 - 280	°C	
Middle Temperature	270 - 290	°C	
Front Temperature	280 - 300	°C	
Nozzle Temperature	270 - 290	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80.0 - 100	°C	
Injection instructions			
Minimum Moisture Content: 0.02 %			
NOTE			
1.	2.0 mm/min		
2.	80*10*4 sp=62mm		
3.	80*10*4		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

