# HIPOL™ B240

### Polypropylene Impact Copolymer

Mitsui Chemicals, Inc.

#### Message:

HIPOL™ B240 is a Polypropylene Impact Copolymer (PP Impact Copolymer) material. It is available in Asia Pacific for blow molding. Important attributes of HIPOL™ B240 are:

Copolymer

Impact Resistant

Typical applications include:

Containers

Engineering/Industrial Parts

Sheet

| General Information                   |                        |          |             |
|---------------------------------------|------------------------|----------|-------------|
| Features                              | Block Copolymer        |          |             |
|                                       | Good Impact Resistance |          |             |
|                                       |                        |          |             |
| Uses                                  | Containers             |          |             |
|                                       | Industrial Parts       |          |             |
|                                       | Sheet                  |          |             |
|                                       |                        |          |             |
| Forms                                 | Pellets                |          |             |
| Processing Method                     | Blow Molding           |          |             |
| Physical                              | Nominal Value          | Unit     | Test Method |
| Density                               | 0.910                  | g/cm³    | ASTM D1505  |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 |                        |          |             |
| kg)                                   | 0.50                   | g/10 min | ASTM D1238  |
| Mechanical                            | Nominal Value          | Unit     | Test Method |
| Tensile Strength                      |                        |          | ASTM D638   |
| Yield                                 | 26.5                   | MPa      |             |
| Break                                 | 24.5                   | MPa      |             |
| Tensile Elongation (Break)            | 500                    | %        | ASTM D638   |
| Impact                                | Nominal Value          | Unit     | Test Method |
| Notched Izod Impact                   |                        |          | ASTM D256   |
| -20°C                                 | 88                     | J/m      |             |
| 0°C                                   | 150                    | J/m      |             |
| 23°C                                  | No Break               |          |             |
| Thermal                               | Nominal Value          | Unit     | Test Method |
| Deflection Temperature Under Load     |                        |          | ASTM D648   |
| 0.45 MPa, Unannealed                  | 100                    | °C       |             |
| 1.8 MPa, Unannealed                   | 55.0                   | °C       |             |
|                                       |                        |          |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

