

Cellidor CP 310-10

Cellulose Acetate Propionate

ALBIS PLASTIC GmbH

Message:

Cellidor CP 310-10 is a Cellulose Acetate Propionate (CAP) product. It is available in Asia Pacific, Europe, or North America. Typical application: Engineering/Industrial Parts.

Characteristics include:

REACH Compliant

RoHS Compliant

Plasticized

Eco-Friendly/Green

General Information			
Additive	Plasticizer		
Features	Non-Phthalate Plasticizer		
	Renewable Resource Content		
Uses	Thick-walled Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (210°C/2.16 kg)	5.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 132/30)	86.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2100	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	50.0	MPa	
Break	45.0	MPa	
Tensile Strain (Break)	15	%	ISO 527-2
Flexural Stress (3.5% Strain)	50.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
--	15	kJ/m²	
-30°C	6.0	kJ/m²	
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
Vicat Softening Temperature	95.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	

Drying Temperature	60.0 to 90.0	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	180 to 230	°C
Mold Temperature	40.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

