

# KRATON® D1184 K

Styrene Butadiene Styrene Block Copolymer

Kraton Polymers LLC

Message:

Kraton D1184 K is a clear, branched triblock copolymer based on styrene and butadiene, with a polystyrene content of 31%. It is supplied from North America in the physical form identified below.

Kraton D1184 K - supplied as a dusted porous pellet

Kraton D1184 KU - supplied as an undusted porous pellet

Kraton D1184 KIM - supplied as a dusted powder

Kraton D1184 K is used as a modifier of bitumen or thermoplastics and in compound formulations. It may also find use as an ingredient in formulating adhesives, sealants and coatings.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
	Copolymer		
Uses	Adhesives		
	Coating Applications		
	Compounding		
	Plastics Modification		
	Sealants		
Appearance	Clear/Transparent		
Forms	Pellets		
	Powder		
Processing Method	Coating		
	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.940	g/cm <sup>3</sup>	ASTM D4025
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	< 1.0	g/10 min	
Antioxidant Additive <sup>1</sup>	0.15 to 0.40	%	Internal Method
Ash Content			Internal Method
KIM	4.0 to 6.0	%	
KT, Talc	0.10 to 0.30	%	
Polystyrene Content	29 to 33	%	Internal Method
Solution Viscosity - Toluene, 15%wt (25°C)	0.90 to 1.3	Pa · s	Internal Method
Total Extractables	< 1.6	%	Internal Method
Volatile Matter	< 1.0	%	Internal Method
Diblock Content	16.0		

Styrene/Rubber ratio	31/69		
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec, Compression Molded)	68		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup> (300% Strain)	5.52	MPa	ASTM D412
Tensile Strength <sup>3</sup> (Yield)	27.6	MPa	ASTM D412
Tensile Elongation <sup>4</sup> (Break)	820	%	ASTM D412
NOTE			
1.	Non-staining phenolic antioxidant		
2.	Measured on films cast from a solution in toluene		
3.	Measured on films cast from a solution in toluene		
4.	Measured on films cast from a solution in toluene		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

