NEFTEKHIM PE 4143L (424F5)

High Density Polyethylene

Nizhnekamskneftekhim Inc.

Message:

Product obtained by gas phase polymerization of ethylene in presence of complex metalorganic catalysts. Stabilization recipe: antacid, antioxidant, thermostabilizer, processing aid, dispersing agent, carbon black. Application: carbon black filled compound for tapes made of blown film.

Technical requirements: TU 2211-145-05766801-2008

General Information			
Additive	Acid Neutralizer		
	Antioxidant		
	Carbon Black		
	Heat Stabilizer		
	Processing Aid		
Features	Acid Resistant		
	Antioxidant		
	Dispersible		
	Good Processability		
	Heat Stabilized		
	High Flow		
	High Strength		
Uses	Film		
	Таре		
Forms	Pellets		
Processing Method	Blown Film		
Physical	Nominal Value	Unit	Test Method
Density	0.940 to 0.944	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	0.40 to 0.60	g/10 min	ASTM D1238
Melt Flow Ratio - MFR 21.6 kg/MFR 2.16 kg	30.0 to 50.0		ASTM D1238
יי			5 . 2 5 5

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

