

Huaxia Shenzhou DS600-B

Perfluoroethylene Propylene Copolymer
Shandong Huaxia Shenzhou New Material Co., Ltd.

Message:

Fluorinated ethylene-propylene (FEP) resin, as a copolymer of tetrafluoroethylene and hexafluoropropylene, has good heat stability, outstanding chemical inertness, excellent electrical insulation and low friction coefficient, and can be processed by a thermoplastic processing method.

Execution standard: Q/DYS 003-2007

General Information		
Features	Copolymer	
	Electrically Insulating	
	General Purpose	
	Good Chemical Resistance	
	Good Thermal Stability	
	Low Friction	
Uses	Film	
	General Purpose	
	Insulation	
	Piping	
	Wire & Cable Applications	
Appearance	Translucent	
Processing Method	Extrusion	
Physical	Nominal Value	Unit
Specific Gravity	2.14 to 2.16	g/cm ³
Melt Mass-Flow Rate (MFR)	8.1 to 12	g/10 min
Volatile Matter	< 0.10	%
Mechanical	Nominal Value	Unit
Tensile Strength	> 21.0	MPa
Tensile Elongation (Break)	> 300	%
Thermal	Nominal Value	Unit
Peak Melting Temperature	255 to 275	°C
Electrical	Nominal Value	
Dielectric Constant (1 MHz)	< 2.15	
Dissipation Factor (1 MHz)	< 7.0E-4	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

