

Halene H P5200UV

High Density Polyethylene

Haldia Petrochemicals Ltd.

Message:

P5200UV is a pipe grade HDPE, produced by the Mitsui CX Technology.

P5200UV is stabilized adequately with HALS+ to give a long service life under outdoor exposure and recommended for telecom ducts.

P5200UV combines excellent processability with good creep resistance, ESCR and mechanical properties.

General Information			
Additive	UV Stabilizer (2000 ppm)		
Features	Good Creep Resistance		
	Good Processability		
	High ESCR (Stress Crack Resist.)		
Uses	Piping		
Processing Method	Pipe Extrusion		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.948	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	0.80	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (10% Igepal, Compression Molded, F50)	> 1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, Compression Molded)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ²			ASTM D638
Yield, Compression Molded	25.0	MPa	
Break, Compression Molded	38.0	MPa	
Tensile Elongation ³			ASTM D638
Yield, Compression Molded	7.0	%	
Break, Compression Molded	750	%	
Flexural Modulus (Compression Molded)	900	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, Compression Molded)	180	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	67.0	°C	ASTM D648
Vicat Softening Temperature	121	°C	ASTM D1525 ⁴
Oxidation Induction Time	> 30	min	ASTM D3895
Extrusion	Nominal Value	Unit	Test Method
Cylinder Zone 1 Temp.	150 to 180	°C	

Cylinder Zone 2 Temp.	150 to 180	°C
Cylinder Zone 3 Temp.	150 to 180	°C
Cylinder Zone 4 Temp.	150 to 180	°C
Cylinder Zone 5 Temp.	150 to 180	°C
Die Temperature	170 to 180	°C

NOTE		
1.	27°C	
2.	50 mm/min	
3.	50 mm/min	
4.	Loading 1 (10 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT