

# PARAPET GR-H24

Polymethyl Methacrylate Acrylic  
Kuraray Co., Ltd.

Message:

PARAPET GR-H24 is a polymethyl methacrylate-acrylic material. This product is available in North America, Europe or Asia Pacific. The main characteristics of PARAPET GR-H24 are: flame retardant/rated flame.

| General Information                                                   |               |                   |                |
|-----------------------------------------------------------------------|---------------|-------------------|----------------|
| Forms                                                                 | Particle      |                   |                |
| Physical                                                              | Nominal Value | Unit              | Test Method    |
| Density                                                               | 1.19          | g/cm <sup>3</sup> | ISO 1183       |
| Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)                              | 10            | g/10 min          | ISO 1133       |
| Molding Shrinkage                                                     | 0.20 - 0.60   | %                 | ISO 294-4      |
| Water Absorption (23°C, 24 hr)                                        | 0.30          | %                 | ISO 62         |
| Hardness                                                              | Nominal Value | Unit              | Test Method    |
| Rockwell Hardness (M-Scale)                                           | 81            |                   | ISO 2039-2     |
| Mechanical                                                            | Nominal Value | Unit              | Test Method    |
| Tensile Modulus                                                       | 2400          | MPa               | ISO 527-2/1A/1 |
| Tensile Stress (Break)                                                | 55.0          | MPa               | ISO 527-2/1A/5 |
| Tensile Strain (Break)                                                | 22            | %                 | ISO 527-2/1A/5 |
| Flexural Modulus                                                      | 2500          | MPa               | ISO 178        |
| Flexural Stress                                                       | 88.0          | MPa               | ISO 178        |
| Impact                                                                | Nominal Value | Unit              | Test Method    |
| Charpy Notched Impact Strength                                        | 2.0           | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy Unnotched Impact Strength                                      | 71            | kJ/m <sup>2</sup> | ISO 179/1eU    |
| Thermal                                                               | Nominal Value | Unit              | Test Method    |
| Heat Deflection Temperature (1.8 MPa, Annealed)                       | 86.0          | °C                | ISO 75-2/A     |
| Vicat Softening Temperature                                           | 94.0          | °C                | ISO 306/B50    |
| Electrical                                                            | Nominal Value | Unit              | Test Method    |
| Surface Resistivity                                                   | 1.0E+16       | ohms              | IEC 60093      |
| Volume Resistivity                                                    | 1.0E+15       | ohms · cm         | IEC 60093      |
| Dielectric Strength                                                   | 20            | kV/mm             | IEC 60243-1    |
| Dielectric Constant (60 Hz)                                           | 4.00          |                   | IEC 60250      |
| Flammability                                                          | Nominal Value | Unit              | Test Method    |
| Flame Rating                                                          | HB            |                   | UL 94          |
| Optical                                                               | Nominal Value |                   | Test Method    |
| Refractive Index                                                      | 1.490         |                   | ISO 489        |
| Additional Information                                                |               |                   |                |
| Light Transmission, ISO 13468-1, 3 mm: >92%Haze, ISO 14782, 3 mm: <1% |               |                   |                |
| Injection                                                             | Nominal Value | Unit              |                |

|                    |             |     |
|--------------------|-------------|-----|
| Drying Temperature | 75.0 - 85.0 | °C  |
| Drying Time        | 4.0 - 6.0   | hr  |
| Rear Temperature   | 220 - 260   | °C  |
| Middle Temperature | 220 - 260   | °C  |
| Front Temperature  | 220 - 260   | °C  |
| Mold Temperature   | 50.0 - 80.0 | °C  |
| Injection Pressure | 70.0 - 150  | MPa |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

