

Sinvicomp SRG6465

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

SINVICOMP SRG6465 is a flexible polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by extrusion. The main characteristics of SINVICOMP SRG6465 are: good rigidity.

The typical application fields of SINVICOMP SRG6465 are: engineering/industrial accessories

General Information			
Features	Rigid, good		
Uses	Washer		
Forms	Particles		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41 - 1.45	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	> 15.0	MPa	ASTM D638
Tensile Elongation (Break)	> 250	%	ASTM D638
Thermal	Nominal Value	Unit	
Low Temperature Brittleness ¹		°C	
Antifungal properties-Fungicide Material	Present		
Additional Information	Nominal Value		
Typical temperature profile for SINVICOMP compound is from 140°C to 160°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.Feeding zone: 140°CMixing zone: 140°C~150°CMetering zone: 150°C~160°CNozzle/Die Zone: 160°C			
NOTE			
1.	Method: GB5470		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT