

HiFill® PA6/6 E4 HS MB

Polyamide 66
Techmer Engineered Solutions

Message:

HiFill® PA6/6 E4 HS MB is a polyamide 66 (nylon 66) product. It can be processed by extrusion and is available in North America.

Features include:

- high viscosity
- heat stabilizer

General Information			
Additive	heat stabilizer		
Features	Thermal Stability		
	Viscosity, High		
Appearance	Available colors		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.8	%	ASTM D955
Water Absorption (24 hr)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	82.7	MPa	ASTM D638
Tensile Elongation (Break)	60	%	ASTM D638
Flexural Modulus	2900	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	237	°C	ASTM D648
1.8 MPa, not annealed	87.8	°C	ASTM D648
CLTE - Flow	7.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms · cm	ASTM D257
Dielectric Strength ¹	18	kV/mm	ASTM D149
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0 - 4.0	hr	

Suggested Max Moisture	0.12	%
Rear Temperature	282 - 293	°C
Middle Temperature	288 - 299	°C
Front Temperature	277 - 288	°C
Nozzle Temperature	282 - 293	°C
Processing (Melt) Temp	282 - 304	°C
Mold Temperature	54.4 - 93.3	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 - 0.689	MPa

Injection instructions

Screw Speed: MediumRecommendations for Molding and Tool Conditions: Well ventedMoisture Content, as received: Product is packaged at 0.2% or less.Recomended Max Moisture: 0.12% down to 0.08%

NOTE


- Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT