

Cevian®-V VF191

Acrylonitrile Butadiene Styrene

Daicel Polymer Ltd.

Message:

Cevian®-V VF191 is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Asia Pacific. Primary attribute of Cevian®-V VF191: Flame Rated.

General Information			
UL YellowCard	E47773-239548		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	19	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	113		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	7.0	kJ/m ²	
23°C	10	kJ/m ²	
Notched Izod Impact			ASTM D256
-30°C, 6.40 mm	60	J/m	
23°C, 6.40 mm	100	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 12.7 mm	90.0	°C	ASTM D648
1.8 MPa, Unannealed	79.0	°C	ISO 75-2/A
Vicat Softening Temperature	97.0	°C	ISO 306/B50
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Ball Pressure Test	90	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (1.50 mm)	27	kV/mm	ASTM D149
Arc Resistance (3.00 mm)	53.0	sec	ASTM D495
Arc Resistance (3.00 mm)	PLC 7		ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.70 mm)	V-2		UL 94

Injection	Nominal Value	Unit
Drying Temperature	70.0 to 80.0	°C
Drying Time	3.0 to 4.0	hr
Rear Temperature	180 to 190	°C
Middle Temperature	200 to 210	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	220 to 230	°C
Mold Temperature	40.0 to 60.0	°C
Back Pressure	5.00 to 15.0	MPa
Screw Speed	40 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

