

AIE PPO 9010-SG30

Polyphenylene Ether + PS

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PPO 9010-SG30 is a Polyphenylene Ether + PS (PPE+PS) material filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of AIE PPO 9010-SG30 are:

- Flame Rated
- Heat Resistant
- High Strength

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	High Heat Resistance		
	High Strength		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Molding Shrinkage	0.30	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	125	MPa	ISO 527-2
Flexural Modulus	6700	MPa	ISO 178
Flexural Stress	155	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	15	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	158	°C	ISO 75-2/B
1.8 MPa, Unannealed	138	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	260 to 310	°C	
Mold Temperature	80.0 to 110	°C	
Injection Pressure	30.0 to 80.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT