

# Jam PE 14ZF8

Linear Low Density Polyethylene  
Jam Petrochemical Company

## Message:

Jam PE 14ZF8 is a Linear Low Density Polyethylene product. It is available in Africa & Middle East. Typical application: Film. Primary characteristic: good processability.

General Information			
Features	Good Processability		
	Terpolymer		
Uses	Film		
Physical	Nominal Value	Unit	Test Method
Density	0.914 to 0.917	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.75	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	
Tensile Strength			ASTM D882
MD : Yield,25 µm, Blown Film	11.0	MPa	
TD : Yield,25 µm, Blown Film	10.9	MPa	
MD : Break, 25 µm,Blown Film	36.0	MPa	
TD : Break, 25 µm,Blown Film	28.0	MPa	
Tensile Elongation			ASTM D882
MD : Break, 25 µm,Blown Film	580	%	
TD : Break, 25 µm,Blown Film	680	%	
Dart Drop Impact (25 µm, Blown Film)	120	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 µm, Blown Film	350	g	
TD : 25 µm, Blown Film	210	g	
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 µm, Blown Film)	30		ASTM D1790
Haze (25.0 µm, Blown Film)	25	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

