

TAROLOX 10 G3 X0

Polybutylene Terephthalate

Taro Plast S.p.A.

Message:

PBT glass fiber reinforced 15%, self extinguishing UL94 V0 also at low thickness, good flow, good surface finish, good mechanical properties.
UL94 V0 approved all colors at 0,97 mm. UL746B approved
Available: all colors, heat stabilized (H), release agent (W), without PBDE/PBDF.

General Information			
UL YellowCard	E143048-223248	E143048-102263588	
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
	Mold Release		
Features	Good Flow		
	Good Mold Release		
	Good Surface Finish		
	Heat Stabilized		
	Self Extinguishing		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52 to 1.54	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.50 to 0.80	%	
Across Flow	0.80 to 1.0	%	
Water Absorption			
23°C, 24 hr	0.050	%	ASTM D570, ISO 62
Saturation	0.30	%	ASTM D570
Saturation, 23°C	0.30	%	ISO 62
Granule Humidity	< 0.050	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5500	MPa	ASTM D638, ISO 527-2
Tensile Strength (Break)	95.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	4.0	%	ASTM D638, ISO 527-2
Flexural Modulus	5500	MPa	ASTM D790, ISO 178
Flexural Stress			

--	140	MPa	ISO 178
Break	140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	4.5	kJ/m ²	ASTM D256, ISO 179
Notched Izod Impact (23°C, 3.20 mm)	60	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	210	°C	ASTM D648, ISO 75-2/B
1.8 MPa, Unannealed	190	°C	ASTM D648, ISO 75-2/A
Continuous Use Temperature			
--	75.0	°C	UL 746B
-- ¹	90.0	°C	IEC 60216
-- ²	120	°C	IEC 60216
-- ³	130	°C	IEC 60216
-- ⁴	160	°C	IEC 60216
Vicat Softening Temperature			
--	210	°C	ASTM D1525, ISO 306/A50 7 ⁵
--	205	°C	ASTM D1525, ISO 306/B50 8 ⁶
Ball Pressure Test (215°C)	Pass		VDE 0470
Melting Temperature	220 to 225	°C	ASTM D211, ISO 121
CLTE - Flow (-30 to 30°C)	3.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (2.00 mm)	22	kV/mm	ASTM D149
Comparative Tracking Index			IEC 60112
Solution A	> 250	V	
Solution B	175	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.970 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature	775	°C	IEC 60695-2-13
Oxygen Index	28	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature			
--	100	°C	
Pre-heater	120 to 130	°C	
Drying Time			
--	1.0 to 2.0	hr	

Pre-heater	3.0	hr
Processing (Melt) Temp	230 to 250	°C
Mold Temperature	80.0 to 110	°C
Injection Rate	Moderate-Fast	

NOTE

1. 20000 hrs
2. Heat Stabilized, 20000 hrs
3. Short Term
4. Heat Stabilized, Short Term
5. Rate A (50°C/h), Loading 1 (10 N)
6. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT