

POLYSTONE® M slide

Ultra High Molecular Weight Polyethylene

Röchling Engineering Plastics SE & Co. KG

Message:

Product characteristics

Very low coefficient of friction

High abrasion and wear resistance

UV-resistant

Typical field of application

Bearing and packing industry

Mechanical engineering

Bottling and food industry

General Information			
Features	Low friction coefficient		
	Good UV resistance		
	Good wear resistance		
	Good wear resistance		
Uses	Engineering application		
	Bottle		
	Food service sector		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	< 0.010	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	64		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	680	MPa	ISO 527-2
Tensile Stress (Yield)	21.0	MPa	ISO 527-2
Tensile Strain (Break)	> 200	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature ¹	< 130	°C	
Melting Temperature	135	°C	ISO 11357-3
CLTE - Flow	1.5E-4 - 2.3E-4	cm/cm/°C	DIN 53752
Specific Heat	1900	J/kg/°C	DIN 52612
Thermal Conductivity	0.40	W/m/K	DIN 52612
Heat Deflection Temperature - Vicat B	79	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+12	ohms·cm	IEC 60093
Dielectric Strength	45	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.00 mm	HB		UL 94
6.00 mm	HB		UL 94
Additional Information			
Service Temperature (Long Term): -250 to 80°C			
NOTE			

1.
- Short Term

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT