## ISOTHANE® 5080A

Thermoplastic Polyurethane Elastomer (Polyether)

Great Eastern Resins Industrial Co Ltd (GRECO)

## Message:

ISOTHANE 5080A product is an 82A, polyether based thermoplastic Polyurethanes. It exhibits excellent bio-compatibility, hydrolytic resistance, fungus resistance and low temperature performance properties. It can be injection molded, blow molded, and extruded. This product is used for biomedical and drug administration applications.

Suggested Applications:

General Information

Wound Dressing, Trans-dermal Patches, IV Bags, Catheter Parts, Medical Tubing and Surgical Gowns.

Features	Biocompatible		
	Fungus Resistant		
	Good Thermal Stability		
	Hydrolytically Stable		
	Low Temperature Resistant		
Uses	Bags		
	Medical/Healthcare Applications		
	Textile Applications		
	Tubing		
Processing Method	Blow Molding		
	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	82		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (H-22 Wheel)	20.0	mg	ASTM D1044
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% Strain	3.60	MPa	
100% Strain	5.40	MPa	
300% Strain	10.0	MPa	
Tensile Strength (Yield)	37.0	MPa	ASTM D412
Tensile Elongation (Break)	620	%	ASTM D412
1			
Tear Strength <sup>1</sup>	80.0	kN/m	ASTM D624

23°C, 22 hr	25	%
70°C, 22 hr	30	%
Extrusion	Nominal Value	Unit
Drying Temperature	93.0	°C
Cylinder Zone 1 Temp.	182 to 193	°C
Cylinder Zone 2 Temp.	188 to 199	°C
Cylinder Zone 3 Temp.	193 to 204	°C
Adapter Temperature	193 to 204	°C
Die Temperature	193 to 210	°C
NOTE		
1.	Die C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

