

RTP 300 HF FR A

Polycarbonate

RTP Company

Message:

High Flow - Unreinforced - Flame Retardant - UL94 V-0

General Information			
UL YellowCard	E84658-251436		
Features	High liquidity		
	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	16 - 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.70 - 0.90	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Moisture Content	0.020	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2280	MPa	ASTM D638
Tensile Strength	55.2	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Flexural Strength	89.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	640	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	132	°C	ASTM D648
1.8 MPa, not annealed	127	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	

Drying Time	4.0	hr
Dew Point	-28.9	°C
Processing (Melt) Temp	288 - 316	°C
Mold Temperature	82.2 - 121	°C
Injection Pressure	68.9 - 103	MPa

Injection instructions

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

