

UBESTA 3030JI5L

Polyamide 12

UBE Industries, Ltd.

Message:

Flexible (Extrusion)

General Information			
Features	Good Flexibility		
Forms	Pellets		
Processing Method	Extrusion		
Part Marking Code	>PA12-HIP<		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	1.4	%	
Flow	0.70	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	26.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	%	ISO 527-2
Flexural Modulus	400	MPa	ISO 178
Flexural Stress	20.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	120	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	45.0	°C	ISO 75-2/A
CLTE - Flow	1.7E-4	cm/cm/°C	ISO 11359-2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT