

# Monprene® CP-38134 XRD1 (PRELIMINARY DATA)

Thermoplastic Elastomer  
Teknor Apex Company

**Message:**  
Monprene CP-38134 XRD1 is a general purpose thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene CP-38134 XRD1 is a low density, low hardness grade that exhibits excellent elastic characteristics. This grade is suitable for both injection molding and extrusion.

General Information			
Features	Low Specific Gravity		
	Without Fillers		
	Low density		
	High elasticity		
	Good adhesion		
	Medium liquidity		
	Good chemical resistance		
	Lubrication		
	Extended tensile rate		
	Hardness, low		
Uses	Handle		
	Films		
	Washer		
	Sporting goods		
	Rubber substitution		
	Consumer goods application field		
	Knob		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
	Natural color		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.878	g/cm <sup>3</sup>	ASTM D792

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 1 sec	35		ASTM D2240
Shaw A, 5 seconds	33		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>1</sup>			ASTM D412
Transverse flow: 100% strain	0.228	MPa	ASTM D412
Flow: 100% strain	0.648	MPa	ASTM D412
Transverse flow: 300% strain	0.386	MPa	ASTM D412
Flow: 300% strain	0.931	MPa	ASTM D412
Tensile Strength <sup>2</sup>			ASTM D412
Transverse flow: Fracture	9.13	MPa	ASTM D412
Flow: Fracture	7.79	MPa	ASTM D412
Tensile Elongation <sup>3</sup>			ASTM D412
Transverse flow: Fracture	> 1000	%	ASTM D412
Flow: Fracture	> 1000	%	ASTM D412
Tear Strength <sup>4</sup>			ASTM D624
Transverse flow	29.6	kN/m	ASTM D624
Flow	30.1	kN/m	ASTM D624
Compression Set <sup>5</sup> (23°C, 22 hr)	14	%	ASTM D395B
Legal statement			

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Rear Temperature	188 - 227	°C
Middle Temperature	188 - 227	°C
Front Temperature	188 - 227	°C
Nozzle Temperature	188 - 227	°C
Processing (Melt) Temp	188 - 227	°C
Mold Temperature	16 - 32	°C
Injection Pressure	1.38 - 5.52	MPa
Injection Rate	Fast	
Back Pressure	0.172 - 0.689	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm
Injection instructions		

无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	177 - 216	°C
Cylinder Zone 2 Temp.	177 - 216	°C
Cylinder Zone 3 Temp.	177 - 216	°C
Cylinder Zone 4 Temp.	177 - 216	°C
Cylinder Zone 5 Temp.	177 - 216	°C
Die Temperature	177 - 216	°C

#### Extrusion instructions

螺杆转速30 - 100 rpm

#### NOTE

- |    |                   |
|----|-------------------|
| 1. | C mold, 510mm/min |
| 2. | C mold, 510mm/min |
| 3. | C mold, 510mm/min |
| 4. | C mold, 510mm/min |
| 5. | Type 1            |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT