

Arnitel® PB582-H

Thermoplastic Copolyester Elastomer
DSM Engineering Plastics

Message:

Arnitel® PB582-H is a Thermoplastic Copolyester Elastomer (TPC-ET) material. It is available in Asia Pacific, Europe, or North America for blow molding.
Primary attribute of Arnitel® PB582-H: Heat Stabilizer.

General Information			
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Uses	Blow Molding Applications		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/10.0 kg)	2.90	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	55		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	300	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	30.0	MPa	
5.0% Strain	11.3	MPa	
10% Strain	16.5	MPa	
50% Strain	22.3	MPa	
100% Strain	26.7	MPa	
Nominal Tensile Strain at Break	150	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	14	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-30°C	12	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	100	°C	ISO 75-2/B
Vicat Softening Temperature	105	°C	ISO 306/B50
Melting Temperature ¹	220	°C	ISO 11357-3
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

