

Hostacom M2 R18 301105

Polypropylene Homopolymer

LyondellBasell Industries

Message:

Hostacom M2 R18 301105 is a mineral filled PP homopolymer, with medium melt flow rate.
This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Filler / Reinforcement	Mineral filler		
Features	Homopolymer		
	Medium liquidity		
Uses	Electrical appliances		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.06	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3200	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	37.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	5.0	%	ISO 527-2
Flexural Modulus ¹ (23°C)	3100	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C	1.5	kJ/m ²	ISO 179/1eA
23°C	2.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
0°C	25	kJ/m ²	ISO 179/1eU
23°C	50	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	62.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT