

LNP™ COLORCOMP™ A1000H compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

LNP COLORCOMP A1000H is an unfilled compound based on ABS. Added feature of this grade is: Healthcare.

Also known as: LNP* COLORCOMP* Compound A-1000 EES HC

Product reorder name: A1000H

General Information			
Uses	Medical/Healthcare Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	5.6	g/10 min	ASTM D1238
220°C/10.0 kg	19	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (220°C/5.0 kg)			
	14.7	cm ³ /10min	ISO 1133
Water Absorption			
			ISO 62
Saturation, 23°C	1.0	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2280	MPa	ASTM D638
--	2530	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	44.1	MPa	ASTM D638
Yield	50.0	MPa	ISO 527-2/5
Break ³	33.8	MPa	ASTM D638
Break	35.3	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	2.6	%	ISO 527-2/5
Break ⁵	24	%	ASTM D638
Break	25	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	2340	MPa	ASTM D790
-- ⁷	2410	MPa	ISO 178
Flexural Stress			
--	76.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	72.4	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	19	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	130	J/m	ASTM D256
23°C	320	J/m	ASTM D256
-30°C ¹⁰	8.5	kJ/m ²	ISO 180/1A
23°C ¹¹	23	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	31.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	94.0	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	80.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹²	80.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	98.0	°C	ASTM D1525 ¹³
--	100	°C	ISO 306/B50, ISO 306/B120
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	8.8E-5	cm/cm/°C	
Transverse : -40 to 40°C	8.8E-5	cm/cm/°C	
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI Str	60.0	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ¹⁴	PLC 6		ASTM D495
High Voltage Arc Tracking Rate (HVTR)	PLC 3		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.52 mm)	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (240°C, 1000 sec ⁻¹)	230	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050 to 0.10	%	
Rear Temperature	182 to 193	°C	
Middle Temperature	193 to 204	°C	
Front Temperature	204 to 216	°C	
Processing (Melt) Temp	199 to 210	°C	
Mold Temperature	10.0 to 48.9	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	

NOTE	
1.	5.0 mm/min
2.	Type I, 5.0 mm/min
3.	Type I, 5.0 mm/min
4.	Type I, 5.0 mm/min
5.	Type I, 5.0 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	Rate B (120°C/h), Loading 2 (50 N)
14.	Tungsten Electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

