

# Kingfa GFPP-R20

Polypropylene

Kingfa

Message:

Kingfa GFPP-R20 is a polypropylene material, which contains a 20% glass fiber reinforced material. This product is available in North America or Asia Pacific.

The main features of Kingfa GFPP-R20 are:

flame retardant/rated flame

high strength

Heat resistance

Typical application areas include:

electrical appliances

engineering/industrial accessories

home apps

Automotive Industry

General Information			
UL YellowCard	E171666-100656956	E171666-320723	
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	High strength		
	Heat resistance, medium		
Uses	Machine/mechanical parts		
	Home appliance components		
	Household goods		
	Application in Automobile Field		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (23°C)	0.40 - 1.1	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (23°C, Injection Molded)	58.0	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break, 23°C, Injection Molded)	3.3	%	ASTM D638
Flexural Modulus <sup>3</sup> (23°C, Injection Molded)	4500	MPa	ASTM D790
Flexural Strength <sup>4</sup> (23°C, Injection Molded)	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	55	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, unannealed, 6.40mm, injection molding	150	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm, injection molding	140	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Additional Information			
Filler Content, ISO3451/1, Method A: 20%			
NOTE			
1.	10 mm/min		
2.	10 mm/min		
3.	2.0 mm/min		
4.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

