# **DENKA POVAL K-17E**

## Polyvinyl Alcohol

## Denka Company Limited

#### Message:

Fully Hydrolzed POVAL

Denka POVAL is soluble in water. The higher the water temperature is, the higher the solubility becomes. It dissolves very little in organic solvent. In addition to suitable viscosity as water-soluble polymer, it has some excellent chracteristics such as bonding strength, surface tension, film formation and mechanical strength of film.

General Information			
Features	Gas Barrier		
	General Purpose		
	Good Adhesion		
	Hydrolysis Resistant		
	Water Soluble		
Uses	Adhesives		
	Coating Applications		
Forms	Granules		
Physical	Nominal Value	Unit	
pH <sup>1</sup> (25°C)	5.0 to 7.0		
Viscosity <sup>2</sup> (20°C)	26 to 32	mPa·s	
Volatile Matter	< 5.0	%	
Degree of Hydrolysis	97.5 to 98.5	mol%	
Sodium Acetate	< 1.0	%	
NOTE			
1.	4 %		
2.	4 %		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

