

SILPURAN® 6740/40 A/B

Silicone
Wacker Chemie AG

Message:

Silicone Rubber, LSR
Gaskets, Plastics and Rubber Processing
Membranes, Pharmaceuticals & Healthcare
Masks, Pharmaceuticals & Healthcare
Seals (HealthCare / Pharma), Pharmaceuticals & Healthcare
Valves (HealthCare / Pharma), Pharmaceuticals & Healthcare

General Information			
Features	Biocompatible		
	BPA Free		
	Breathable		
	Good Chemical Resistance		
	Good Flexibility		
	Good Sterilizability		
	Good Thermal Stability		
	High Gas Permeability		
	High Heat Resistance		
	High Purity		
	Low to No Odor		
	Low to No Water Absorption		
	Non-Toxic		
	Steam Resistant		
Uses	Body Implants		
	Medical Devices		
	Medical/Healthcare Applications		
	Pharmaceuticals		
Agency Ratings	ISO 10993		
	USP Class VI		
Processing Method	Injection Molding		
	Liquid Injection Molding (LIM)		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Viscosity	400	Pa · s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method

Shore Hardness (Shore A)	38		DIN 53505
Tensile Strength	9.20	MPa	DIN 53504
Tensile Elongation at Break	710	%	DIN 53504
Tear Strength	25.0	kN/m	ASTM D624B

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

