# Yuyao PBT 4028G30

### Polybutylene Terephthalate

Yuyao Tenglong Plastics Co., Ltd.

#### Message:

Yuyao PBT 4028G30 is a Polybutylene Terephthalate (PBT) product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PBT 4028G30 include electrical/electronic applications, automotive and engineering/industrial parts. Characteristics include: Flame Rated Flame Retardant Creep Resistant Fatigue Resistant Good Dimensional Stability

General Information					
Additive	Flame Retardant				
Features	Electrically Insulating				
	Fatigue Resistant				
	Flame Retardant				
	Good Creep Resistance				
	Good Dimensional Stability				
	Good Impact Resistance				
	Good Processability				
	High Heat Resistance				
Uses	Automotive Applications				
	Automotive Under the Hood				
	Connectors				
	Electrical Parts				
	Printed Circuit Boards				
	Valves/Valve Parts				
Appearance	Colors Available				
Processing Method	Injection Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.50	g/cm³	ASTM D792		
Molding Shrinkage - Flow	1.5 to 2.8	%	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength	70.0	MPa	ASTM D638		
Tensile Elongation (Break)	3.0	%	ASTM D638		
Flexural Modulus	2840	MPa	ASTM D790		
Flexural Strength	80.0	MPa	ASTM D790		
Impact	Nominal Value	Unit	Test Method		

Notched Izod Impact (Area)	10.0	kJ/m²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	70.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	115 to 120	°C	
Drying Time	6.0 to 8.0	hr	
Processing (Melt) Temp	230 to 255	°C	
Mold Temperature	60.0 to 100	°C	
Injection Pressure	70.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

