

Bapolene® LL3039 BLK

Linear Low Density Polyethylene

Bamberger Polymers, Inc.

Message:

Bapolene LL3039F BLK is a black LLDPE compound specifically designed for rotational molding applications. It offers excellent Environmental Stress Cracking Resistance, warp resistance, and impact strength. It is available in pellet or powder form. UV stabilized. This product meets FDA standards for food contact applications.

General Information			
Additive	UV stabilizer		
Features	High ESCR (Stress Cracking Resistance)		
	Bending resistance		
	Impact resistance, high		
	Good UV resistance		
	Compliance of Food Exposure		
Uses	Industrial water tank		
	Agricultural water tank		
	Outdoor application		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Black		
Forms	Powder		
	Particle		
Processing Method	rotomolding		
Physical	Nominal Value	Unit	Test Method
Density	0.939	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			ASTM D1693B
10% Igepal, F50	> 500	hr	ASTM D1693B
100% Igepal, F50	1000	hr	ASTM D1693B
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	17.2	MPa	ASTM D638
Tensile Elongation ² (Break)	780	%	ASTM D638
Flexural Modulus - 2% Secant	760	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	53.0	°C	ASTM D648
1.8 MPa, not annealed	39.5	°C	ASTM D648

Vicat Softening Temperature	112	°C	ASTM D1525
Additional Information			
ARM Impact, 1/8 in, -40°C: 51 ft-lbARM Impact, 1/4 in, -40°C: 176 ft-lb			
NOTE			
1.	20 mm/min		
2.	20 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

