

# ElectriPlast® EP-SS/PP

Polypropylene

Integral Technologies, Inc.

## Message:

ElectriPlast® EP-SS/PP is a polypropylene product that contains stainless steel fibers. It can be processed by injection molding and is available in North America. The main characteristics are: flame retardant/rated flame.

General Information			
Filler / Reinforcement	Stainless steel fiber		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2290	MPa	ASTM D638
Tensile Strength (Break)	21.0	MPa	ASTM D638
Tensile Elongation (Break)	19	%	ASTM D638
Flexural Modulus	2110	MPa	ASTM D790
Flexural Strength	33.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	79	J/m	ASTM D256
Unnotched Izod Impact (23°C)	370	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	52	ohms	ESD STM11.11
Volume Resistivity	16	ohms · cm	ASTM D257
Static Decay	10	msec	Internal method
Surface Resistance	5.0	ohms	ESD STM11.11
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 16	mm/min	UL 94
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0	hr	
Rear Temperature	232	°C	
Middle Temperature	238	°C	
Front Temperature	238	°C	
Nozzle Temperature	232	°C	
Mold Temperature	37.8	°C	
Back Pressure	1.76	MPa	

Screw Speed	170	rpm
Injection instructions		

Injection Speed: 1 in/sec1st Stage (injection): 2400 psi2nd Stage (molding): 500 psiDecomposition: 0.5 inch

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT