## NuSil CV-2189-2

## Silicone

NuSil Technology

## Message:

Controlled Volatility (CV) Silicone Materials

Silicone's ability to remain elastic at low temperatures and resistant to breakdown at high temperatures offer excellent utility in extraterrestrial environments where materials are repeatedly exposed to extreme temperatures. NuSil's Controlled Volatility (CV) and Ultra Low Outgassing TM (SCV) silicone products are used by leading space programs to provide the much-needed resilient protection they require against contamination and material degradation.

Benefits of Silicone Materials for Space Broad Operating Temperature Compensation for CTE Mismatch Protection Against Atomic Oxygen Optically Clear Formulations Flight Legacy Comments: Thixotropic

General Information		
Features	Low to No Outgassing	
	Thixotropic	
Uses	Adhesives	
	Aerospace Applications	
	Electrical/Electronic Applications	
	Sealants	
Agency Ratings	ASTM E 595	
	NASA SP-R-0022A	
Additional Information	Nominal Value	Unit
Cure System	Platinum	
Uncured Properties	Nominal Value	Unit
Color	Black	
Density	1.15	g/cm³
Viscosity	230	Pa·s
Curing Time (200°C)	0.25	hr
Cured Properties	Nominal Value	Unit
Shore Hardness (Shore A)	17	
Tensile Strength	5.17	MPa
Tensile Elongation at Break	700	%
Tear Strength	9.63	kN/m

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

