

Evoprene™ COGEE 638

Styrene Ethylene Butylene Styrene Block Copolymer

AlphaGary

Message:

The Evoprene COGEE range was specially developed to provide materials which will comould or coextrude to engineering thermoplastics (ETPs). This enables, for example, polyamide (nylon) handles or ABS housings to be given a soft touch feel whilst polycarbonate lenses can have gaskets moulded on to provide a weathertight product.

The Evoprene COGEE grades are modified Kraton G based compounds. Many of the characteristics exhibited by the Evoprene G and Evoprene Super G ranges are shown by Evoprene COGEE compounds. However, they do have to be processed quite differently to obtain optimum bond strengths and performance characteristics.

General Information			
Features	Good Weather Resistance		
	Ozone Resistant		
Uses	Soft Touch Applications		
Processing Method	Coextrusion		
	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm ³	ISO 2781

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	65		ISO 868

Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	165	mm ³	DIN 53516
Service Temperature	-30 to 60	°C	
Bond Strength	1.77	MPa	Internal Method
M-S Flow	0.883	MPa	Internal Method
Ozone Resistance ¹ (35°C)	No Cracks		ISO 1431-1
UV Rating ² (40°C)	No Visible Cracks or Crazing		

Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	2.50	MPa	
300% Strain	4.30	MPa	
Tensile Stress (Yield)	5.80	MPa	ISO 37
Tensile Elongation (Break)	400	%	ISO 37
Tear Strength ³	48	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	50	%	
70°C, 22 hr	88	%	
100°C, 22 hr	87	%	

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (125°C, 336 hr)	-10	%	ISO 1817
Change in Tensile Strain at Break in Air (125°C, 336 hr)	1.0	%	ISO 1817
Change in Shore Hardness in Air (125°C, 336 hr)	1.0		ISO 1817
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Regrind	20	%	
Rear Temperature	250 to 270	°C	
Middle Temperature	250 to 270	°C	
Front Temperature	250 to 270	°C	
Nozzle Temperature	250 to 270	°C	
Processing (Melt) Temp	280	°C	
Mold Temperature	30.0 to 60.0	°C	
Injection Rate	Fast		
Vent Depth	0.020 to 0.050	mm	
NOTE			
1.	100 pphm/200 hrs/20% Strain		
2.	350 hrs		
3.	Method Ba, Angle (Unnicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT