

NORYL™ APS130 resin

Polyphenylene Sulfide + PPE

SABIC Innovative Plastics Asia Pacific

Message:

NORYL™ APS130 resin is a Polyphenylene Sulfide + PPE (PPS+PPE) material. It is available in Asia Pacific for injection molding.

General Information			
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/5.0 kg)	29	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.25 to 0.70	%	Internal Method
Water Absorption (24 hr)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	113	MPa	Internal Method
Tensile Elongation (Break)	8.0	%	Internal Method
Flexural Modulus	8430	MPa	ASTM D790
Flexural Strength	157	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	267	°C	ASTM D648
CLTE - Flow (-30 to 30°C)	2.5E-5 to 5.5E-5	cm/cm/°C	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Dielectric Strength (1.60 mm, in Oil)	22	kV/mm	ASTM D149
Dielectric Constant			ASTM D150
50 Hz	3.30		
60 Hz	3.30		
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0 to 8.0	hr	
Drying Time, Maximum	24	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	282 to 316	°C	
Middle Temperature	288 to 321	°C	
Front Temperature	293 to 327	°C	
Nozzle Temperature	299 to 332	°C	

Processing (Melt) Temp	299 to 332	°C
Mold Temperature	93.3 to 149	°C
Back Pressure	0.689 to 1.38	MPa
Screw Speed	50 to 100	rpm
Vent Depth	0.025 to 0.076	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT