# Hifax HKC 426P BLACK

## Polypropylene Homopolymer

### LyondellBasell Industries

#### Message:

"Hifax" HKC 426P Black is a 20% mineral filled PP homopolymer incl. UV package for automotiveexterior use. Use e.g. for cowl-vent grills.

General Information			
Filler / Reinforcement	Mineral,20% Filler by Weight		
Features	Good Stiffness		
	Good UV Resistance		
	Homopolymer		
	Low Warpage		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	11	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16			
kg)	12.0	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	32.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	5.0	%	ISO 527-2/50
Flexural Modulus - Secant	2800	MPa	ISO 178

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd. Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

