

RAMOFIN PPC717

Polypropylene Copolymer
Polyram Ram-On Industries

Message:
UV STABILIZED POLYPROPYLENE COPOLYMER FOR INJECTION MOULDING APPLICATIONS.

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238, ISO 1133
Water Absorption			
Saturation	> 0.030	%	ASTM D570
Saturated, 23°C	> 0.030	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	78		ASTM D785
R scale	78		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	25.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	300	%	ASTM D638, ISO 527-2
Flexural Modulus	1100	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	600	J/m	ASTM D256
23°C	50	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	148	°C	ISO 75-2/B
1.8 MPa, not annealed	80.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	148	°C	ASTM D1525
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+19	ohms · cm	IEC 60093
Dielectric Strength	500	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.30		IEC 60250
Injection	Nominal Value	Unit	

Rear Temperature	190 - 220	°C
Middle Temperature	200 - 225	°C
Front Temperature	205 - 230	°C
Mold Temperature	30.0 - 65.0	°C
Injection Pressure	70.0 - 105	MPa
Holding Pressure	35.0 - 70.0	MPa
Back Pressure	0.350 - 0.700	MPa
Screw Speed	60 - 90	rpm
Injection instructions		

Fill Speed: 25 to 50 mm/sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

