

DOMAMID® A1-506-V15-I1-N

Polyamide 6

DOMO Engineering Plastics GmbH

Message:

Polyamide 6, 15 % glass fiber reinforced, impact modified, natural

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	40.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹			ISO 294-4
Across Flow : 23°C, 72 hr	1.0	%	
Flow : 23°C, 72 hr	0.70	%	
Ash Content (650°C)	15	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5200	MPa	ISO 527-2/1A/1
Tensile Stress			ISO 527-2/1A/5
Yield	110	MPa	
Break	110	MPa	
Tensile Strain (Break)	3.5	%	ISO 527-2/1A/20
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	80	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	221	°C	ISO 11357-3
NOTE			

1. 50%RH, between 16 to 72 hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

