

# TOTAL Polyethylene Aceso® PEM 2408

Low Density Polyethylene  
TOTAL Refining & Chemicals

Message:

Aceso® PEM 2408 is a low density polyethylene made by a high pressure autoclave process without antioxidant. This grade is particularly suitable for the blown film, injection blow molding and extrusion blow molding processes.

Aceso® PEM 2408 has been specifically designed for the manufacture of healthcare products and pharmaceutical packaging like bags, pouches, blow-fill-seal applications, medical films, tubes, etc... However it is recommended to contact your local sales representative to obtain specific information and individual certificates regarding compliance to regulations.

General Information	
Features	Low density
Uses	Blown Film
	Films
	Bags
	Pipe fittings
	Drug packaging
	Medical/nursing supplies
Agency Ratings	EC 1907/2006 (REACH)
RoHS Compliance	RoHS compliance
Forms	Particle
Processing Method	Blow film
	Extrusion blow molding
	Injection blowing molding

Physical	Nominal Value	Unit	Test Method
Density	0.924	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.80	g/10 min	ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	99.0	°C	ISO 306
Melting Temperature	111	°C	ISO 11357-3
Extrusion	Nominal Value	Unit	
Melt Temperature	160 - 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

