

RTV-2 P-125

Silicone Rubber, RTV-2

Silicones, Inc.

Message:

P-125 is a translucent, high tear strength, platinum-catalyzed, RTV-2 silicone rubber, which was designed for casting parts where visual inspection is required. It is easy to mix and de-air, and will cure with virtually no shrinkage. The speed at which the rubber hardens can be dramatically accelerated with heat or with Pt Accelerator at room temperature. Addition-cure two-component silicone rubbers exhibit excellent chemical and heat resistance, but may show some inhibition sensitivity. P-125 is extremely useful for prototype applications where superior mechanical properties are required.

General Information			
Features	Good Chemical Resistance		
	High Heat Resistance		
Forms	Liquid		
Physical	Nominal Value	Unit	
Specific Gravity	1.09	g/cm ³	
Thermal	Nominal Value	Unit	
Service Temperature - Cured	-51 to 316	°C	
Coverage - Cured	0.925	cm ³ /g	
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
Hardener	Mix Ratio by Weight: 1.0		
	Mix Ratio by Volume: 11		
Resin	Mix Ratio by Weight: 10		
	Mix Ratio by Volume: 100		
Shelf Life	26	wk	
Thermoset Mix Viscosity ¹	90000 to 110000	cP	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- ²	Clear/Transparent		
-- ³	Translucent		
Viscosity			
-- ⁴	1.0 to 2.0	Pa·s	
-- ⁵	160 to 180	Pa·s	
Curing Time	16 to 24	hr	
Pot Life	60 to 120	min	

Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness			
Shore A ⁶	36 to 44		
Shore A ⁷	36 to 44		
Tensile Strength	4.48 to 5.17	MPa	ASTM D412
Tensile Elongation at Break	200 to 300	%	ASTM D412
Tear Strength	13.1 to 18.4	kN/m	ASTM D624
Electric Strength	20	kV/mm	
Relative Permittivity (100 Hz)	2.90		
Volume Resistivity	1.0E+15	ohms·cm	
Dissipation Factor (100 Hz)	3.0E-3		

NOTE

- | | |
|----|-----------|
| 1. | Mixed |
| 2. | Activator |
| 3. | Base |
| 4. | Activator |
| 5. | Base |
| 6. | 7 Days |
| 7. | 1 Day |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT