

# Viton® F-605C

Fluoroelastomer  
DuPont Performance Elastomers

Message:  
Curative Containing Pre-compounds.  
Precompound for compression molding.

General Information			
Features	Solvent resistance		
	Bending resistance		
	acid resistance		
	Steam resistance		
	Compliance of Food Exposure		
Uses	Washer		
	Metal bonding		
Agency Ratings	FDA 21 CFR 177.2600 2		
Forms	Particle		
Processing Method	Extrusion		
	Compression molding		
	Calendering		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.90	g/cm <sup>3</sup>	ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Compression Set (200°C, 70 hr)	28	%	ASTM D395
Additional Information			

Nominal Viscosity, ML 1 + 10, 121°C: 60Polymer Fluorine Content: 70.0%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT