

LITEN MB 73

Polyethylene Homopolymer
UNIPETROL RPA

Message:

LITEN MB 73 is a linear polyethylene, homopolymer with narrow molecular weight distribution and higher melt flow, intended for injection moulding. It is suitable for manufacture of various types of crates, household articles, etc.

LITEN MB 73 meets the hygienic requirements on materials and articles intended for contact with foodstuffs according to Regulation (EC) 1935/2004 of the European Parliament and of the Council, as well as according to Commission Regulation (EU) No 10/2011 including changes and additions.

General Information			
Features	High Flow		
	Homopolymer		
	Narrow Molecular Weight Distribution		
Uses	Crates		
	Household Goods		
Agency Ratings	EC 1935/2004		
	EU 10/2011		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.963	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	11	g/10 min	
190°C/5.0 kg	30	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	58		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	25.0	MPa	ISO 527-2
Tensile Strain (Yield)	9.0	%	ISO 527-2
Flexural Modulus	1150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	126	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

