

Estane® 58137 TPU

Thermoplastic Polyurethane Elastomer (Polyester)

Lubrizol Advanced Materials, Inc.

Message:

Type: Estane® 58137 is a 65D Polyester Thermoplastic Polyurethane (TPU).

Features: Fast cycling, broad temperature performance, and durability

Use: Injection Molding

General Information			
Features	Fast molding cycle		
	Durability		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow			ASTM D955
-- ¹	0.80	%	ASTM D955
-- ²	0.90	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 5 sec)	62 - 68		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C)	370	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	41.0	mg	ASTM D3389
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% strain, 0.762mm	21.0	MPa	ASTM D412
300% strain, 0.762mm	31.0	MPa	ASTM D412
Tensile Strength (Break, 0.762 mm)	41.0	MPa	ASTM D412
Tensile Elongation (Break, 0.762 mm)	430	%	ASTM D412
Tear Strength			
0.762 mm ³	206	kN/m	ASTM D624
Cracking	51	kN/m	ASTM D470
Compression Set			ASTM D395
23°C, 22 hr	42	%	ASTM D395
70°C, 22 hr	61	%	ASTM D395
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-15.0	°C	DSC
Melting Temperature	227	°C	DSC

Injection	Nominal Value	Unit
Drying Temperature	104	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	210	°C
Middle Temperature	221	°C
Front Temperature	229	°C
Nozzle Temperature	232	°C
Processing (Melt) Temp	232	°C
Injection Pressure	69.0 - 103	MPa
Injection Rate	Moderate	
Holding Pressure	35.0 - 69.0	MPa
Back Pressure	0.345	MPa
Screw Speed	60 - 100	rpm

Injection instructions

Air Dew Point: -40°C

NOTE

1. Flex Bar
2. Disc
3. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

