# **ESTADIENE 0835 GF**

### Acrylonitrile Butadiene Styrene

Cossa Polimeri S.r.l.

#### Message:

**Heat Resistant** 

ESTADIENE 0835 GF is an Acrylonitrile Butadiene Styrene (ABS) product filled with 17% glass fiber. It is available in Europe. Applications of ESTADIENE 0835 GF include automotive and engineering/industrial parts.

Characteristics include:

Flame Rated Good Dimensional Stability Good Processability

General Information			
Filler / Reinforcement	Glass Fiber,17% Filler by Weight		
Features	Good Dimensional Stability		
	Good Processability		
	High Heat Resistance		
Uses	Automotive Applications		
	Engineering Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	70.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	5300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	60	J/m	
23°C	70	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
	117	°C	ASTM D1525 <sup>1</sup>
	108	°C	ASTM D1525 <sup>2</sup>
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	НВ		

3.20 mm	НВ		
Glow Wire Ignition Temperature (2.00 mm)	650	°C	IEC 60695-2-13
NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

