

EnCom PC 1214 UV

Polycarbonate

EnCom, Inc.

Message:

General Purpose V-2 PC with UV

General Information	
Additive	UV Stabilizer
Features	General Purpose
Uses	Automotive Applications
	Business Equipment
	Thin-walled Parts
Appearance	Black
	Colors Available
	Natural Color
Forms	Pellets
Processing Method	Injection Molding
	Profile Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	55.2	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Flexural Strength (Yield)	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	750	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	135	°C	
1.8 MPa, Unannealed	129	°C	
Flammability	Nominal Value	Test Method	
Flame Rating (3.18 mm)	V-2	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	93.3 to 121	°C	

Drying Time	4.0	hr
Drying Time, Maximum	7.0	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 75	%
Rear Temperature	271 to 293	°C
Middle Temperature	282 to 304	°C
Front Temperature	288 to 316	°C
Nozzle Temperature	288 to 310	°C
Processing (Melt) Temp	293 to 316	°C
Mold Temperature	71.1 to 98.9	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	30 to 70	rpm
Vent Depth	0.038 to 0.076	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

