

Pebax® 2533 SD 02

Polyether Block Amide

Arkema

Message:

Polyether block amide PEBAX® 2533 SD 02 is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This SD grade is heat and UV stabilized and contains mould release additive.

General Information			
Additive	Mold Release		
	UV Stabilizer		
Uses	Gears		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Across Flow : 24 hr, 4.00 mm	0.80	%	
Flow : 24 hr, 4.00 mm	0.50	%	
Water Absorption			ISO 62
23°C, 24 hr	1.2	%	
Equilibrium, 23°C, 50% RH	0.40	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A	77		
Shore A, 15 sec	74		
Shore D	27		
Shore D, 15 sec	22		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	32.0	MPa	ISO 527-2
Tensile Strain (Break)	> 750	%	ISO 527-2
Flexural Modulus	12.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Charpy Unnotched Impact Strength			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	58.0	°C	ISO 306

Melting Temperature	134	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	55.0 to 65.0	°C	
Drying Time	4.0 to 8.0	hr	
Processing (Melt) Temp	180 to 240	°C	
Mold Temperature	10.0 to 30.0	°C	
NOTE			
1.	Mold at 40°C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

