

# Huaфон JF-W-6110

Polyurethane  
Huaфон Group Co., Ltd.

Message:

General Wet Process PU Resin with Hydrolysis Resistance

Characteristics

Mid hard type, 24 hours hydrolysis resistance, uniform cell structure, high peeling strength, good elasticity, good fullness.

Applications

Shoes, Bags

General Information		
Features	High Elasticity	
	Hydrolysis Resistant	
	Medium Hardness	
Uses	Bags	
	Footwear	
Additional Information	Nominal Value	Unit
Solvents	DMF	
Uncured Properties	Nominal Value	Unit
Solids Content	29 to 31	%
Viscosity (25°C)	180 to 260	Pa·s
Cured Properties	Nominal Value	Unit
Tensile Modulus (100% Secant)	10.0 to 12.0	MPa
Tensile Strength	> 20.0	MPa
Tensile Elongation at Break	> 200	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT