

RTP ESD A 1500-55D

Thermoplastic Polyester Elastomer

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Features	ESD Protection		
RoHS Compliance	Contact Manufacturer		
Appearance	Black		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm, Injection Molded)	1.3 to 1.7	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	8.00	MPa	ASTM D412
Tensile Elongation (Break)	10	%	ASTM D412
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+11	ohms	ASTM D257
Volume Resistivity	5.0E+8	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Rear Temperature	193 to 232	°C	
Middle Temperature	193 to 232	°C	
Front Temperature	193 to 232	°C	
Mold Temperature	21.0 to 49.0	°C	
Injection Pressure	69.0 to 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

