

Durethan® BKV 50 H2.0 EF 900116

Polyamide 6

LANXESS GmbH

Message:

PA 6, 50 % glass fibers, injection molding, improved flowability, heat-aging stabilized

General Information				
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight			
Additive	heat stabilizer			
Features	Good liquidity			
	Thermal Stability			
Agency Ratings	EC 1907/2006 (REACH)			
Processing Method	Injection molding			
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.57	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.080	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.19	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.040	--	%	ISO 2577
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	232	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	16200	10000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	215	140	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.7	3.5	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	15000	9900	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	340	230	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.1	4.4	%	ISO 178/A
ISO Shortname	PA 6, GHR, 10-160, GF50	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	95	85	kJ/m ²	ISO 179/1eU

23°C	100	85	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	15	--	kJ/m ²	ISO 180/1A
23°C	17	20	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	85	80	kJ/m ²	ISO 180/1U
23°C	85	80	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	3.40	--	J	ISO 6603-2
23°C	4.30	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	1000	--	N	ISO 6603-2
23°C	1180	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	210	--	°C	ISO 75-2/A
8.0 MPa, not annealed	180	--	°C	ISO 75-2/C
Vicat Softening Temperature	214	--	°C	ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	1.2E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (23°C)	7.0E+14	4.0E+11	ohms·cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	35	34	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.70	12.9		IEC 60250
23°C, 1 MHz	4.20	4.80		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	0.014	0.26		IEC 60250
23°C, 1 MHz	0.017	0.077		IEC 60250
Comparative Tracking Index (Solution A)	400	--	V	IEC 60112
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	

Processing (Melt) Temp	270 - 290	°C
Mold Temperature	80.0 - 120	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

