

STRANOX H-PP40%LFT

Polypropylene Homopolymer

Oxford Polymers

Message:

STRANOX H-PP40%LFT is a Polypropylene Homopolymer (PP Homopolymer) material filled with 40% long glass fiber. It is available in North America.
Primary attribute of STRANOX H-PP40%LFT: Homopolymer.

General Information			
Filler / Reinforcement	Long Glass Fiber,40% Filler by Weight		
Features	Homopolymer		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	124	MPa	ASTM D638
Tensile Elongation (Yield)	2.5	%	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Flexural Strength	159	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	300	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	163	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT