

ExxonMobil™ LDPE LD 654

Low Density Polyethylene Resin

ExxonMobil Chemical

Message:

LD 654 is a very high fluidity low density polyethylene grade and has excellent flexibility. It can be added to low-fluidity low-density polyethylene grades to improve their processability.

General Information			
Hardness	Nominal Value	Test Method	
Durometer Hardness (Shore D, 15 sec)	39	ISO 868	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	84.0	MPa	ISO 527-2/1A/1
Tensile Stress (100% Strain)	7.30	MPa	ISO 527-2/1A/50
Tensile Strain (Break)	> 100	%	ISO 527-2/1A/50
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	75.0	°C	ISO 306

Legal statement

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

