# ALTECH® PA66 A 2030/588 GF30

### Polyamide 66

#### ALBIS PLASTIC GmbH

#### Message:

ALTECH® PA66 A 2030/588 GF30 is a Polyamide 66 (Nylon 66) product filled with 30% glass fiber. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Typical application: Automotive.

Characteristics include:

**REACH Compliant** 

**RoHS Compliant** 

**Chemical Resistant** 

Good Mold Release

Heat Stabilizer

General Information			
UL YellowCard	E80168-101630986		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Flow		
	Good Mold Release		
	Heat Stabilized		
	Oil Resistant		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.37	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9300	MPa	ISO 527-2
Tensile Stress	160	MPa	ISO 527-2
Tensile Strain (Break)	2.6	%	ISO 527-2
Flexural Modulus	8600	MPa	ISO 178
Flexural Stress	240	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	50	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	255	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	80.0	°C	
Drying Time - Desiccant Dryer	8.0 to 12	hr	

Suggested Max Moisture	0.15	%
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 120	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

