

# HIPOL™ F600

Polypropylene

Mitsui Chemicals, Inc.

## Message:

HIPOL™ F600 is a Polypropylene material. It is available in Asia Pacific. Primary attribute of HIPOL™ F600: Rigid.

Typical applications include:

Film

Packaging

General Information			
Features	High Rigidity		
Uses	Film		
	Food Packaging		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	37.3	MPa	
Break	24.5	MPa	
Tensile Elongation (Break)	500	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	20	J/m	
23°C	25	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	110	°C	
1.8 MPa, Unannealed	65.0	°C	
Vicat Softening Temperature	155	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

